



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 23, 2019

Mr. Paul Bullock
INTEGRA INTERNATIONAL FABRICS
3650 Ralph Ellis Blvd.
Loris, SC 29569

Reference: Laboratory Test Report
Lab Identification No. 35597
Invoice No. 66754

Dear Mr. Bullock:

One (1) fabric sample, identified as SOLARO, was received and tested in accordance with CAN/ULC-S109-14, “Standard for Flame Tests of Flame-Resistant Fabrics and Films”, Small-Flame Test. The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>		<u>Damaged Length (mm)</u>	
	<u>Residual Flame (sec)</u>		<u>Warp</u>	<u>Fill</u>
1	0.0	0.0	193	97
2	0.0	0.0	124	91
3	0.0	0.0	104	102
4	0.0	0.0	99	102
5	0.0	0.0	109	99
Avg.			112	

The fabric sample submitted **meets** the minimum requirements of the Small-Flame Test. The maximum average damaged length shall not exceed 165 millimeters and the maximum damaged length for any individual specimen shall not exceed 190 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 23, 2019

Mr. Paul Bullock
INTEGRA INTERNATIONAL FABRICS
3650 Ralph Ellis Blvd.
Loris, SC 29569

Reference: Laboratory Test Report
Lab Identification No. 35597
Invoice No. 66754

Dear Mr. Bullock:

One (1) fabric sample, identified as **TAI-DIMOUT**, was received and tested in accordance with CAN/ULC-S109-14, “Standard for Flame Tests of Flame-Resistant Fabrics and Films”, Large-Flame Test. The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (Seconds)</u>	<u>Char Length (Millimeters)</u>
Length 1	0.0	64
Length 2	0.0	76
Width 1	0.0	102
Width 2	0.0	114

The fabric sample submitted meets the minimum requirements of the Large-Flame Test. The length of char on the individual folded specimens shall not exceed 635 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

