

SÖZAL

Standard: FLAME RETARDANT TEST
Company: INTEGRA FABRICS

Design: VOGUE
Colour ID: 602,603,604,608

Sample	Mass before the test (g)	Mass after the test (g)	Mass Loss %
1	10,28	9,59	6,71
2	10,22	9,43	7,73
3	10,23	9,86	3,62
4	10,30	10,01	2,82
5	10,28	8,96	12,84
6	10,62	10,13	4,61
7	10,44	10,15	2,78
8	10,30	9,70	5,83
9	10,24	9,76	4,69
10	10,65	9,62	9,67
Avarage	10,36	9,72	6,13

Results

- i)Fragments or residues of specimens that fall to the floor did not continue to burn for more than 2 seconds
- ii)Avarage weight did not loss exceed 40 %.

PASSED

***This test has been applied regarding NFPA 701 Test Method 1 test standarts**

***Above mentioned results are for your information.**

5

BURCU ERDOĞRU / HANDE ATILA/19.02.2016

KOSAB Güvenli Sk. No.7 Kestel / Bursa / Türkiye T: +90 224 331 51 53 - 54 - 55 F: +90 224 331 51 59

www.sozal.com.tr