

WORLDWIDE SERVICE

-"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 28, 2019

Mr. Paul Bullock INTEGRA INTERNATIONAL FABRICS 3650 Ralph Ellis Blvd. Loris, SC 29569

Reference: Laboratory Test Report

Lab Identification No. 36142

Invoice No. 67313

Dear Mr. Bullock:

One (1) fabric sample, identified as **WATERFALL**, was received and tested in accordance with CAN/ULC-S109-14, "Standard for Flame Tests of Flame-Resistant Fabrics and Films", Small-Flame Test. The results are as follows:

<u>Test Results</u>					
Specimen Number	Residual Flame (sec)		Damaged Length (mm)		
	<u>Warp</u>	<u>Fill</u>	<u>Warp</u>	<u>Fill</u>	
1	0.0	0.0	127	172	
2	0.0	0.0	134	120	
3	0.0	0.0	157	117	
4	0.0	0.0	145	112	
5	0.0	0.0	142	155	
Ava.			138		

The fabric sample submitted **meets** the minimum requirements of the Small-Flame Test. The maximum average damaged length shall not exceed 165 millimeters and the maximum damaged length for any individual specimen shall not exceed 190 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

"We Test Per Your Request"———

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 28, 2019

Mr. Paul Bullock INTEGRA INTERNATIONAL FABRICS 3650 Ralph Ellis Blvd. Loris, SC 29569

Reference: Laboratory Test Report

Lab Identification No. 36142

Invoice No. 67313

Dear Mr. Bullock:

One (1) fabric sample, identified as **WATERFALL**, was received and tested in accordance with CAN/ULC-S109-14, "Standard for Flame Tests of Flame-Resistant Fabrics and Films", Large-Flame Test. The results are as follows:

Specimen Numb	<u>Residual Flame (Seconds)</u>	Char Length (Millimeters)
Length 1	0.0	102
Length 2	0.0	76
Width 1	0.0	140
Width 2	0.0	114

The fabric sample submitted **meets** the minimum requirements of the Large-Flame Test. The length of char on the individual folded specimens shall not exceed 635 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr