



DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 6, 2014

Ms. Laine Dickson
INTEGRA INTERNATIONAL FABRICS
3650 Ralph Ellis Blvd.
Loris, SC 29569

Reference: Laboratory Test Report
Lab Identification No. 10166
Invoice No. 40938 (Attached)

Dear Ms. Dickson:

One (1) fabric sample, identified as **AMBIANCE**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2010 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	19.33
2	0.0	13.80
3	0.0	14.76
4	0.0	12.01
5	0.0	11.86
6	0.0	17.02
7	0.0	14.06
8	0.0	8.88
9	0.0	20.04
10	0.0	21.04
AVG.	0.0	15.28


The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr
Attachment

**DIVERSIFIED****TESTING LABORATORIES, INC.**
WORLDWIDE SERVICE

"We Test Per Your Request" →

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 6, 2014

Ms. Laine Dickson
INTEGRA INTERNATIONAL FABRICS
3650 Ralph Ellis Blvd.
Loris, SC 29569Reference: Laboratory Test Report
Lab Identification No. 10165
Invoice No. 40937 (Attached)

Dear Ms. Dickson:

One (1) fabric sample, identified as **TAI DIMOUT #2021260**, was received and tested to quantitatively assess light blocking properties in accordance with AATCC 148-1989, "Light Blocking Effect of Curtain Materials". The amount of transmitted light through the sample was recorded and calculated into % transmission. The test results are as follows:

% Transmitted Light @ 100 foot candles

0.1%

% Blocked Light (Opacity) @ 100 foot candles

99.9%

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr
Attachment