

**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
 P.O. BOX 4004  
 BURLINGTON, NORTH CAROLINA 27215  
 PHONE (336) 227-7710 • FAX (336) 227-1175  
 www.diversifiedtestinglabs.com

May 14, 2019

Reference: Laboratory Test Report  
 Lab Identification No. 36036  
 Invoice No. 67218

One (1) fabric sample, identified as **EVE FR**, was received and tested in accordance with CAN/ULC-S109- 14, "Standard for Flame Tests of Flame-Resistant Fabrics and Films", Small-Flame Test. The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>			
	<u>Residual Flame (sec)</u>		<u>Damaged Length (mm)</u>	
	<u>Warp</u>	<u>Fill</u>	<u>Warp</u>	<u>Fill</u>
1	0.0	0.0	110	118
2	0.0	0.0	146	109
3	0.0	0.0	137	119
4	0.0	0.0	139	145
5	0.0	0.0	141	143
Avg.			131	

The fabric sample submitted **meets** the minimum requirements of the Small-Flame Test. The maximum average damaged length shall not exceed 165 millimeters and the maximum damaged length for any individual specimen shall not exceed 190 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

May 14, 2019

Reference: Laboratory Test Report  
Lab Identification No. 36036  
Invoice No. 67218

One (1) fabric sample, identified as **EVE FR**, was received and tested in accordance with CAN/ULC-S109-14, “Standard for Flame Tests of Flame-Resistant Fabrics and Films”, Large-Flame Test. The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame (Seconds)</u>	<u>Char Length (Millimeters)</u>
Length 1	0.0	229
Length 2	0.0	152
Width 1	0.0	152
Width 2	0.0	279

The fabric sample submitted meets the minimum requirements of the Large-Flame Test. The length of char on the individual folded specimens shall not exceed 635 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

