



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

October 28, 2019

Mr. Paul Bullock  
INTEGRA INTERNATIONAL FABRICS  
3650 Ralph Ellis Blvd.  
Loris, SC 29569

Reference: Laboratory Test Report  
Lab Identification No. 38642  
Invoice No. 69806

Dear Mr. Bullock:

One (1) fabric sample, identified as **LOUISA**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>	
	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	15.64
2	0.0	13.54
3	0.0	9.48
4	0.0	20.62
5	0.0	21.55
6	0.0	4.48
7	0.0	21.49
8	0.0	21.30
9	0.0	16.57
<u>10</u>	<u>0.0</u>	<u>22.18</u>
AVG	0.0	16.68

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

