



DIVERSIFIED
TESTING LABORATORIES, INC.
 WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

August 10, 2017

Mr. Paul Bullock
 INTEGRA INTERNATIONAL FABRICS
 3650 Ralph Ellis Blvd.
 Loris, SC 29569

Reference: Laboratory Test Report
 Lab Identification No. 26496
 Invoice No. 57698

Dear Mr. Bullock:

One (1) fabric sample, identified as **LUXE KT**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>	
	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	18.11
2	0.0	20.52
3	0.0	16.05
4	0.0	14.56
5	0.0	11.02
6	0.0	11.86
7	0.0	12.11
8	0.0	16.30
9	0.0	20.29
<u>10</u>	<u>0.0</u>	<u>7.16</u>
AVG	0.0	14.80

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

